

Standard recipe

Ebeam evaporator

Material	Pressure	Soak 2	Power	Rate
Ti	9.00E-06		5	2
Cr	9.00E-06		5	2
Ni	9.00E-06		5	2
Al	9.00E-06		10	2
Au	9.00E-06		30	2
Pt	9.00E-06		30	2
Pd	9.00E-06		10	2
Ge	9.00E-06		5	2