

Standard recipe

ICP-F

Material	SF6	CHF3	Ar	Pressure	ICP	Bias	Rate (nm/min)	Table Temp
Si	2	4	10	0.3	100	70	40	20