

## Standard Recipe

## P-ALD

Material	Process	cycle	N2 Purge	cycle	N2 Purge	Cycles	Comments
TiN	Plasma	Ti 0.1s	4s	NH3 30.5s	10s	100	
ZnN	Plasma	Zn 0.1s	4s	NH3 30.5s	10s	150	
TaN	Plasma	Ta 1.6s	8s	NH3 30.5s	10s	200	
AlN	Plasma	Al 0.1s	4s	NH3 30.5s	10s	100	