

Standard recipe

ICP-F

Material	CHF3	Pressure	ICP	Bias	Rate (nm/min)	Table Temp
Al2O3	10	0.1	100	70	30	20